

## Listing of Claims

1. (Withdrawn) A fuel cell bipolarplate for providing a gas flow path while being disposed at both sides of MEA, comprising:

a bipolarplate substrate that is of only a corrosion-resisting metallic material or a composite composed of a corrosion-resisting metallic material to define the surface layer of the composite and the other metallic material to define the inner layer of the composite; and

a conductive contact layer that is formed on the bipolarplate substrate, the conductive contact layer being of noble metal and having a thickness of 0.0005  $\mu\text{m}$  or greater and less than 0.01  $\mu\text{m}$ .

2. (Currently Amended) A fuel cell bipolarplate for providing a gas flow path while being disposed at both sides of MEA, comprising:

a bipolarplate substrate that is of only a corrosion-resisting metallic material or a composite composed of a corrosion-resisting metallic material to define the surface layer of the composite and the other metallic material to define the inner layer of the composite;

a joining layer being of Ti, Ni, Ta, Nb or ~~[[PT]]~~ Pt; and

a conductive contact layer that is formed through the joining layer on the bipolarplate substrate, the conductive contact layer being any one of TiN, TiC and TiB or a composite of two or more of TiN, TiC and TiB ~~of a composite compound~~ with a bandgap of 0.6 eV or less and having a thickness of 0.0005  $\mu\text{m}$  or greater and less than 0.01  $\mu\text{m}$ .

3. (Withdrawn) The fuel cell bipolarplate according to claim 1, wherein:

the conductive contact layer is formed through a joining layer on the bipolarplate substrate.

4. (Canceled)

5. (Withdrawn) The fuel cell bipolarplate according to claim 1, wherein:  
the conductive contact layer is formed only on a rib face to contact a conductive gas diffusion layer of MEA.

6. (Original) The fuel cell bipolarplate according to claim 2, wherein:  
the conductive contact layer is formed only on a rib face to contact a conductive gas diffusion layer of MEA.

7. (Withdrawn) The fuel cell bipolarplate according to claim 1, wherein:  
the corrosion-resisting metallic material is Ti or Ti alloys.

8. (Original) The fuel cell bipolarplate according to claim 2, wherein:  
the corrosion-resisting metallic material is Ti or Ti alloys.

9. (Withdrawn) The fuel cell bipolarplate according to claim 7, wherein:  
the conductive contact layer is of Au, Pt, Ru or Pd.

10. (Canceled)

11. (Withdrawn) The fuel cell bipolarplate according to claim 9, wherein:

the conductive contact layer is formed through a joining layer on the bipolarplate substrate, and the joining layer is of Ti, Ni, Ta, Nb or Pt and has a thickness of 0.6 nm or greater and 50 nm or less.

12. (Currently Amended) The fuel cell bipolarplate according to ~~claim 10~~ claim 2, wherein:

the joining layer has a thickness of 0.6 nm or greater and 50 nm or less.

13. (Withdrawn) The fuel cell bipolarplate according to claim 9, wherein:

the conductive contact layer is formed only on a rib face to contact a conductive gas diffusion layer of MEA, and a groove portion other than the rib face is covered with titanium oxide.

14. (Currently Amended) The fuel cell bipolarplate according to ~~claim 10~~ claim 2, wherein:

the conductive contact layer is formed only on a rib face to contact a conductive gas diffusion layer of MEA, and a groove portion other than the rib face is covered with titanium oxide.